

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ :

C09K 17/52

A1

(11) International Publication Number:

WO 96/09355

(43) International Publication Date:

28 March 1996 (28.03.96)

(21) International Application Number:

PCT/NL95/00315

(22) International Filing Date:

22 September 1995 (22.09.95)

(30) Priority Data:

9401542

22 September 1994 (22.09.94) NL

(71)(72) Applicant and Inventor: BASTIAANSEN, Antonius, Johannes, Maria [NL/NL]; Seminarielaan 10, NL-4741 DL Hoeven (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): HANZEN, Andries [NL/NL]; Memmonietenweg 43, NL-6702 AK Wageningen (NL). DE WIT, Dirk [NL/NL]; Halderweg 64, NL-6721 ZK Bennekom (NL). TOURNOIS, Huibert [NL/NL]; Jan van Arkelweg 20, NL-3911 CD Rhenen (NL).

(74) Agents: DE BRUIJN, Leendert, C. et al.; Nederlandsch Octrooibureau, Scheveningsweg 82, P.O. Box 29720, NL-2502 LS The Hague (NL).

(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).

Published

With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: COVERING MATERIAL FOR AGRICULTURAL AND HORTICULTURAL SOIL

(57) Abstract

The invention provides a covering material for agricultural soil, which material contains starch or a derivative or fraction thereof as binder together with a structure-improving amount of an acid and/or an oil, and a finely divided vegetable filler such as straw. The oil is for instance palm oil or linseed oil in an amount of 1-25 wt. %. The acid is preferably 0.2-4 % by weight of phosphoric acid or citric acid. The material may further comprise fungicides, bentonite and/or rubber latices.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Covering material for agricultural and horticultural soil

The invention relates to a weed-inhibiting covering material, for agricultural soil, which contains a polymer carbohydrate and a vegetable filler.

5 A covering material of this type is disclosed in Netherlands Patent Application 8402655. Said known material consists of a suspension of, for example, cellulose waste (paper) as filler, carboxymethylcellulose or polyvinyl acetate as binder and, in addition, a light-absorbent agent, such as soot, and inhibits the growth of grasses.

10 According to Swiss Patent 678478, ground in parks and gardens can be protected against weeds by applying a layer of material consisting of felted paper residues, optionally mixed with polystyrene foam. Netherlands patents 91383 and 98116 teach the use of hydroxyalkyl and carboxymethyl starches and swelling starch, respectively, for protecting soil against erosion.

15 However, the protective effect of the known covering materials is of relatively short duration. Furthermore, these materials also contain poorly degradable constituents (polyvinyl acetate, polystyrene) and mould formation often takes place in the material in the course of time.

20 A covering material has now been found which is inexpensive, provides long-lasting (many months) protection against the growth of weeds, protects the soil against erosion and, furthermore, can be applied easily and is completely biodegradable.

The covering material, for agricultural soil, according to the invention therefore contains a polymer carbohydrate as binder and a finely divided vegetable filler and is characterised in that the binder is starch or a fraction or derivative thereof together with a structure-improving amount of an acid and/or an oil.

25 Surprisingly it has been found that water uptake is lower, even at high RH (relative atmospheric humidity) and, partly as a result of this, the protective effect of the covering material is appreciably better when the polymer carbohydrate used is starch or a fraction or derivative thereof with improved structure. The covering material according to the invention is effective in controlling grasses, weeds, mosses and other undesirable plants, reduces erosion, saves irrigation water and may also promote plant growth.

30 In this context, agricultural soil is understood to be any soil on which crops can be cultivated, either in the field outdoors or in greenhouses, optionally in trays or pots. Agricultural soil therefore also includes, for example, horticultural soil, (tree) nursery

soil, garden soil and potting compost. The soil concerned is in the main natural, optionally cultivated vegetable compost, but also completely or partially synthetic compost.

The polymer carbohydrate binder can consist of starch or a fraction or derivative thereof, for at least 50 wt.% or even at least 75 wt.%. Fractions and derivatives are understood to be decomposition products such as amylose and amylopectin and partially depolymerised products, and physically and chemically modified products, such as extruded, dried, oxidised, hydroxyalkylated, carboxymethylated and acetylated starches, and depolymerised, crystallised starches and other forms. Carboxymethyl-starch, native (unmodified) starch, extruded starch and in particular roller-dried starch, which can be converted to a starch solution in cold water and can be obtained, inter alia, under the name Flocgel Ivw, have been found to be suitable, amongst others. A polymer carbohydrate means here a carbohydrate having at least 15, especially at least 25 monosaccharide units. In addition to the starch material, the binder may also comprise cellulose and hemicellulose, and derivatives and fractions thereof.

In particular, the structure of the starch material can be improved and the drying thereof can be promoted by adding an oil to it. The term oil should be understood to comprise glycerol esters, in particular triglycerides of medium and long-chain fatty acids. It comprises fats and oils which are liquid at ambient temperature, but also fats that have higher melting points, such as between ambient temperature and about 75°C.

The oil is advantageously a vegetable oil. Vegetable oils which can be used are, for example, linseed oil, rape oil, sunflower oil, coconut oil, palm oil and palm kernel oil. The oil preferably has a melting range above ambient temperature, and in particular between 25 °C and 50 °C. Palm oil is the most preferred because it has a favourable melting range and is hydrolysed to only a slight extent. Linseed oil is another preferred oil. Mixtures of oils can also be used. The amount of oil to be used is, for example, 1 - 25 % by weight, preferably 5 - 20 % by weight and particularly preferentially 8 - 15 % by weight, based on the dry covering material. The oil can be added by simple mixing, after melting if applicable. The oil can also be added by extrusion, e.g. if it is a solid fat.

Alternatively, or in combination, the structure and the weed-resistant effect of the starch material can be improved by the addition of acid. The use of an acid is especially preferred under relatively high humidity conditions. The acid used in the

SUBSTITUTE SHEET (RULE 26)

covering material according to the invention is an acid which does not leach out quickly. Examples of such acids are phosphoric acid, oxalic acid, succinic acid, lactic acid, malic acid, benzoic acid, citric acid, gluconic acid, and the like, the preference being for citric acid and phosphoric acid, and the greatest preference being for phosphoric acid. Combinations with these and other acids are also readily possible. The total amount of acid is preferably 0.2 - 4 % by weight, in particular 1 - 1.5 % by weight, based on the entire dry mixture.

Suitable fillers are virtually all finely divided vegetable fillers, such as chaff, straw, hay, hemp, paper and wood. The particle size of the filler is found to be important. If the particles are too large, the layer of covering material becomes too thick and can be more difficult to apply. The particle size is preferably such that the filler passes through a sieve with a mesh size of 2.5 mm and more preferentially passes through a 1 mm sieve. However, the particles must also not be too small, because the drying properties of the filler then become inadequate. Preferably the particles do not pass through a 0.1 mm sieve, and in particular do not pass through a 0.25 mm sieve. Outstanding results have been recorded with finely divided straw having an average particle size of 0.5 - 1 mm. The vegetable filler can be crushed in any desired way, for example using a hammer mill, pin mill or cutter mill. In the case of straw, the best results are obtained with a hammer mill.

The weight ratio of filler to binder can vary from, for example, 10 : 1 to 1 : 2, in particular from 4 : 1 to 1 : 1, based on solids.

It was found that the performance of the covering material can be further improved by incorporation of a clay mineral. Suitable clay minerals include e.g. bentonite. The clay mineral may be added in an amount of 3 - 30 %, especially 5 - 25 % by weight, with respect to the total weight of dry binder and filler material and optional oil. The clay mineral causes the covering layer to be stronger and more resistant to rain.

Furthermore it was found that the addition of a latex material improves the resistance of the covering material to rain and wear, whereas the biodegradability was still fully satisfactory. The latex material is preferably a natural latex such as rubber latex, but it may also be a synthetic latex if this is sufficiently degradable, such as a poly(hydroxyalkanoic acid). The latex can be added in an amount of 2 - 30 %, especially 4 - 20 % by weight, with respect to the total weight of dry binder and filler material and optional oil.

SUBSTITUTE SHEET (RULE 26)

If necessary, the covering material can contain other constituents, for example in order further to control undesired plant growth and/or mould growth. For instance, the material can contain a light-absorbent substance, for example carbon, or a fungicide. In general a fungicide will not be needed if the covering is used outdoors, in the open field, but will frequently be needed if the material is used in a greenhouse. Examples of acceptable and effective fungicides are imazalil (especially for starch), azaconazole and propiconazole (especially for cellulose) and cycloheximide. Other possible additives are, for example, plasticisers such as urea or glycerol. All constituents of the covering material must be biodegradable, that is to say must have been completely decomposed, under the influence of organisms present in the ground, into harmless substances within a period of, for example, 6 months to a year.

The covering material can be prepared by mixing all dry constituents, optionally with the exception of the latex if used. The acid can be added at this stage or at a later stage. At the location where the covering layer is applied, the dry mixture can be mixed with a suitable amount of water or other solvent, such that an easily spreadable suspension or slurry is obtained. In general, 5 - 10 parts of dry mixture are introduced into 90 - 95 parts of water. The liquid constituents, including, if necessary, the acid and the latex, are added thereto and the whole is mixed. The suspension is then spread over the soil using an amount of 100 - 1000 g/m² (10 - 100 kg/are), in particular 300 - 700 g/m², and dried slowly (for example over a period of 1 - 4 days). A robust layer 1 - 6 mm thick is thus obtained, which remains intact for several (2 - 24) months and effectively inhibits weeds.

Any pouring, spraying or atomising installation can be used for application of the slurry or suspension. One example is an atomiser which contains a disc which rotates about a vertical shaft, the suspension being poured onto said disc and then being strewn in all directions at high speed in atomised form by said disc and spread uniformly over the soil.

Example 1

A mixture of 58.7 % by weight of finely divided chaff with an average particle size of 0.5-1 mm was mixed with 29.3 % by weight of physically destructed potato starch (Flocgel lv) and 10.6 % by weight of palm oil. The mixture was mixed with water in a weight ratio of 1 : 10.

SUBSTITUTE SHEET (RULE 26)

The suspension was mechanically spread over cultivation soil in a ratio of 650 g/m² (dry matter) and after drying for about 3 days formed a robust layer of about 4 mm thick, which was not washed away by rain and prevented the growth of grasses and other undesirable plants for several months.

5

Example 2

A mixture was prepared according to example 1, to which furthermore 1.4 % by weight (with respect to the total dry matter) of citric acid was added. The suspension formed a robust layer of about 4 mm thick after about 3 days and prevented the growth of grasses and other undesirable plants for several months including wet periods.

10

Example 3

A mixture of 58.7 % by weight of finely divided straw with an average particle size of 0.5 - 1 mm, 29.3 % by weight roller-dried potato starch (Flocgel Ivw) and 10.6 % by weight palm oil was prepared. The mixture was mixed with water in a weight ratio of 1 : 10.

15

The resulting suspension was mechanically sprayed in an amount of 500 g/m² (solids) over compost and after drying for about three days formed a robust layer of about 3 mm thick which was not washed away even in a downpour and also prevented the growth of grasses and other undesirable plants for at least 1 season.

20

Example 4

A mixture was prepared according to example 3, and 1.4 % by weight (based on the total dry mixture) of 85 % phosphoric acid was added.

25

The suspension was dry within 3 days even at high atmospheric humidity and was about 3 mm thick after drying. It was not washed away by downpour and prevented the growth of grasses and other undesirable plants for at least 1 season.

Example 5

A mixture was prepared according to example 3, and 10 % by weight (based on the total dry mixture) of natural rubber latex was added. After application a dry layer of about 3 mm thick after drying. It was not washed away by downpour and prevented the growth of grasses and other undesirable plants for at least 1 season.

30

Claims

1. Covering material for agricultural soil, which contains a polymer carbohydrate as a binder and a finely divided vegetable filler, characterised in that the material contains starch or a derivative or fraction thereof as binder together with a structure-improving amount of an acid and/or an oil.
2. Covering material according to claim 1, wherein said material comprises an oil, and said structure-improving amount is 1 - 25% by weight of the dry covering material.
3. Covering material according to Claim 1 or 2, wherein said material comprises an acid and said structure-improving amount is 0.2 - 4 % by weight.
4. Covering material according to Claim 3, wherein the acid is phosphoric acid or citric acid.
5. Covering material according to one of Claims 1 - 4, wherein the binder is starch which can be converted to a starch solution in cold water.
6. Covering material according to one of Claims 1 - 5, wherein the filler is straw, hemp, paper or chaff.
7. Covering material according to Claim 6, wherein the filler is straw with an average particle size of 0.25 mm to 1 mm.
8. Covering material according to one of Claims 1 - 7, wherein the material also contains, based on solids, 5 - 20 % by weight of an oil, in particular palm oil.
9. Covering material according to one of Claims 1 - 8, wherein the material also contains a fungicide.
10. Covering material according to one of Claims 1 - 9, wherein the material also contains 2-30 % by weight of a natural rubber latex.
11. Method for protecting crops against weeds, wherein a covering material according to one of Claims 1-10 is applied in an amount of 100 - 1000, especially 300 - 700 g/m², based on solids, to the soil in which the crops are growing.

SUBSTITUTE SHEET (RULE 26)

INTERNATIONAL SEARCH REPORT

Internat Application No
PCT/NL 95/00315

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09K17/52

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09K A01G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	NL,A,98 116 (N.V.W.A.SCHOLTENS) 15 October 1956 see column 1, line 7 - line 16 see column 1, line 34 - column 2, line 21	1,5,9
Y	see column 3, line 49 - column 4, line 17 ---	3,6,11
X	NL,A,91 383 (N.V. W.A.SCHOLTENS) 15 March 1956 see column 1, line 7 - line 18 see column 1, line 26 - column 2, line 6	1,5,9
Y	see column 4, line 25 - column 5, line 14 ---	3,6,11
Y	DE,A,34 31 565 (Z.PECHAN) 21 March 1985 see claims 1,3,4,7 see page 4, line 32 - page 5, line 31; example 11 ---	1,6,11
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"A" document member of the same patent family

Date of the actual completion of the international search

9 January 1996

Date of mailing of the international search report

15.01.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Boulon, A

INTERNATIONAL SEARCH REPORT

Internat Application No
PCT/NL 95/00315

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	DE,A,42 00 855 (H.STÖVER) 22 July 1993 see column 1, line 1 - line 36 see column 2, line 39 - line 53 ---	1,6,11
Y	US,A,3 881 278 (O.R.VIDEEN) 6 May 1975 see column 1, line 58 - column 2, line 27 see column 4, line 6 - line 17; claims 1-4 ---	1,6,11
Y	WO,A,90 13598 (T.NACHTMAN) 15 November 1990 see page 2, line 1 - line 26 see page 3, line 19 - page 5, line 34 -----	1,6,11

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat. Application No

PCT/NL 95/00315

Patent document
cited in search report

Publication
date

Patent family
member(s)

Publication
date

NL-A-98116

BE-A-	527489	
DE-C-	963690	
FR-A-	1143558	02-10-57
GB-A-	786265	
NL-C-	91383	
NL-B-	177068	
US-A-	2957834	25-10-60

NL-A-91383

BE-A-	527489	
DE-C-	963690	
FR-A-	1143558	02-10-57
GB-A-	786265	
NL-C-	98116	
NL-B-	177068	
US-A-	2957834	25-10-60

DE-A-3431565

21-03-85

FR-A-	2558035	19-07-85
NL-A-	8402655	01-04-85

DE-A-4200855

22-07-93

NONE

US-A-3881278

06-05-75

NONE

WO-A-9013598

15-11-90

AU-B-	637103	20-05-93
AU-B-	5677490	29-11-90
CA-A-	2032501	11-11-90
EP-A-	0424523	02-05-91
GR-B-	1000765	30-12-92
IE-B-	62623	22-02-95
JP-T-	4500697	06-02-92
US-A-	5082500	21-01-92